

PA6-CF30 HS

WJ PA6-CF30 HS is a carbon-fibre reinforced PA6 filament. Review its grade-specific reference properties, printing parameters and handling guidance.

WJ-TDS-PA6-CF30-HS-001 | V1.0 | 2026-10-20 | EN

Physical & thermal properties

Property	Test method	Unit	Typical value
Density	ISO 1183	g/cm³	1.26
Light transmission	N/A	-	N/A
Flame retardancy	N/A	-	N/A
Melting temperature	ISO 11357	°C	260
Heat deflection temperature (0.45 MPa)	ISO 75-2	°C	178
Vicat softening temperature (A50)	ISO 75-2	°C	N/A

Mechanical properties

Property	Test method	Unit	Typical value
Tensile strength (X-Y)	ISO 527	MPa	85
Tensile strength (Z)	ISO 527	MPa	46
Elongation at break (X-Y)	ISO 527	%	3.9
Elongation at break (Z)	ISO 527	%	2
Bending strength (X-Y)	ISO 178	MPa	159
Bending strength (Z)	ISO 178	MPa	76
Bending modulus (X-Y)	ISO 178	MPa	8028
Bending modulus (Z)	ISO 178	MPa	1577
Charpy impact strength (X-Y)	ISO 179	KJ/m²	33
Charpy impact strength (Z)	ISO 179	KJ/m²	11

This technical data sheet provides typical reference values for material comparison and selection only. It is not an independent third-party test report and does not constitute a product specification, warranty or guarantee of performance. Test methods and specimen conditions are stated in the corresponding sections. The user must verify suitability for the intended application.

PA6-CF30 HS

Recommended printing parameters

Parameter	Unit	Value
Nozzle temperature	°C	275
Bed temperature	°C	100
Build surface material	-	PEI film, PI film
Cooling fan	-	OFF
Printing speed	mm/s	120-150
Environmental temperature	°C	40-60
Annealing (after printing)	°C	100-120
Annealing time	-	Not specified in the supplied reference sheet.

Recommended parameters are based on Bambu Studio with a 0.4 mm nozzle. Printing conditions may differ with other nozzle diameters.

Storage & handling

Topic	Guidance
Nozzle wear	Use a wear-resistant nozzle, such as hardened steel or ruby. Brass nozzles are susceptible to wear.
Drying and moisture	Dry before printing. Store and print in dry conditions below 20% relative humidity. Drying temperature and duration are not specified in the supplied reference sheet.
Self-support removal	When using this filament as its own support material, remove supports before excessive moisture uptake; otherwise supports may bond permanently to the model.
Annealing	After printing, anneal the part at 100-120 °C to improve overall strength. Annealing duration is not specified in the supplied reference sheet.

PA6-CF30 HS

Data source & conditions

Topic	Data source & test conditions
Data status	Typical reference values; not independently re-tested by WJ on this batch.
Reference revision	LW-TDS-A01; WJ edition V1.0.
Printing conditions	Recommended parameters are based on Bambu Studio with a 0.4 mm nozzle. Printing conditions may differ with other nozzle diameters.
Unspecified conditions	Specimen conditioning, infill, perimeter count, drying schedule and annealing duration are not specified in the supplied reference sheet.
Orientation labels	X-Y and Z labels are retained from the supplied reference sheet. Detailed specimen preparation is not specified.

Disclaimer & data status

Typical values are for reference and comparison only, not for design specifications or quality control. Actual properties depend on part design, environment, printing conditions and post-processing. Specifications may change without notice. The user must assess safety, compliance, technical suitability and end-of-life disposal or recycling for the intended application. WJ makes no warranty of suitability and accepts no liability for damage, injury or loss arising from use.

This technical data sheet provides typical reference values for material comparison and selection only. It is not an independent third-party test report and does not constitute a product specification, warranty or guarantee of performance. Test methods and specimen conditions are stated in the corresponding sections. The user must verify suitability for the intended application.

Carbon-fibre reinforced PA6. Fibre content is not specified in the supplied reference sheet.

WJ-TDS-PA6-CF30-HS-001 | V1.0 | A1 | 2026-10-20