



PETG-CF

Carbon-Fibre Reinforced PETG · stiffer, low-warp structural filament

1.75 mm ± 0.03

1 kg net

OEM / ODM

Document no.	WJ-TDS-PETGCF-001
Revision	V1.0
Issue date	2026-08-01
Supersedes	None (first issue)

1. DESCRIPTION

WJ PETG-CF adds chopped carbon fibre to a PETG base, overcoming the relatively low stiffness of standard PETG while keeping the low warping and easy bed adhesion that make PETG popular. The fibre reinforcement raises flexural and tensile performance and gives parts a matte, fibre-textured finish. With a heat deflection temperature of approximately 105 °C at 0.45 MPa, it suits structural, load-bearing parts that need more rigidity than PETG or PLA+ without moving to a high-temperature engineering polymer.

Typical applications

structural brackets and enclosures, drone frames, jigs and fixtures, and functional prototypes that need extra stiffness over standard PETG while keeping easy, low-warp printing.

Processing summary

the carbon fibre is abrasive, so a hardened or diamond-tipped nozzle is recommended. PETG-CF prints almost as easily as standard PETG · moderate cooling and a clean glass or PEI bed give good adhesion without an enclosure.

- Drying before printing 65 °C for 8 h
- Nozzle size 0.4 (0.6 recommended) mm and above
- Nozzle temperature 250 · 270 °C
- Build plate temperature 90 · 110 °C
- Part cooling fan Medium to high
- Printing speed 40 · 150 mm/s

2. PRODUCT SPECIFICATION

typical, not a specification for acceptance

Parameter	Unit	Value
Filament diameter	mm	1.75
Diameter tolerance	mm	± 0.03
Net filament weight	kg	1
Spool material	·	PC + ABS spool, Ø 200 × 65 mm, hub Ø 55 mm, heat resistant to 90 °C
Spool size (Ø × H)	mm	Ø 200 × 65 mm
Colour range	·	Stock colours as listed on the product page; RAL / Pantone matching and custom colour development on request

Values are typical for the grade and are subject to normal manufacturing tolerance. Colour masterbatch is not included in the base polymer content.

3. RECOMMENDED PRINTING PARAMETERS

starting point, not a guarantee

Parameter	Unit	Value
Drying before printing	°C / h	65 °C for 8 h
Printing and storage humidity	·	Dry storage; sealed with desiccant
Nozzle size	mm	at least 0.4 (0.6 recommended)
Nozzle type	·	Hardened steel / diamond tip (required)
Nozzle temperature	°C	250 · 270
Build plate type	·	Glass or PEI

Parameter	Unit	Value
Bed surface preparation	·	Clean; light adhesive if needed
Bed temperature	°C	90 · 110
Part cooling fan	·	Medium to high
Printing speed	mm/s	40 · 150
Enclosed chamber	·	Not required
Chamber temperature	°C	25 · 45
Retraction length / speed	mm / mm/s	0.6 · 1.0 mm / 20 · 40 mm/s
Max overhang angle	°	~ 70
Max bridging length	mm	~ 30

4. MATERIAL PROPERTIES

specimens per section 5

Values are typical results from tests on specimens printed and conditioned as described in Section 5. They are not a guarantee of performance of any individual printed part.

4.1 Physical and thermal properties

Property	Test method	Unit	Typical value
Density	ISO 1183	g/cm ³	~ 1.25
Melt flow rate (MFR)	210 °C, 2.16 kg	g/10 min	~ 1.4 ± 0.2
Melting temperature	DSC	°C	~ 250
Glass transition temperature	DSC	°C	~ 80
Vicat softening temperature	ISO 306	°C	~ 85
Heat deflection temperature	ISO 75, 0.45 MPa	°C	~ 105
Heat deflection temperature	ISO 75, 1.8 MPa	°C	~ 95
Saturated water absorption	25 °C, 55 % RH	%	~ 0.3

4.2 Mechanical properties

Property	Test method	Unit	Typical value
Young's modulus (X·Y)	ISO 527 / GB/T 1040	MPa	~ 2500 ± 150
Young's modulus (Z)	ISO 527 / GB/T 1040	MPa	~ 1900 ± 150
Tensile strength (X·Y)	ISO 527 / GB/T 1040	MPa	~ 50 ± 4
Tensile strength (Z)	ISO 527 / GB/T 1040	MPa	~ 45 ± 4
Elongation at break (X·Y)	ISO 527 / GB/T 1040	%	~ 12
Elongation at break (Z)	ISO 527 / GB/T 1040	%	~ 6
Flexural modulus	ISO 178 / GB/T 9341	MPa	~ 2700 ± 130
Flexural strength	ISO 178 / GB/T 9341	MPa	~ 80 ± 5
Impact strength, notched	ISO 179 / GB/T 1043	kJ/m ²	~ 6.5
Impact strength, unnotched	ISO 179 / GB/T 1043	kJ/m ²	~ 16

4.3 Chemical and physical characteristics

Parameter	Value
Composition	Carbon-fibre reinforced PETG (PETG-CF)
Odour	Slight odour when printing
Skin hazard	Cut fibre ends can be sharp · gloves recommended
Chemical stability	Stable under normal storage and handling
Solubility	Insoluble in water
UV and weathering resistance	Moderate · similar to standard PETG
Acid resistance	Resistant to dilute acids
Alkali resistance	Resistant to dilute bases
Organic solvent resistance	Not resistant to some organic solvents
Oil and grease resistance	Resistant to common oils and greases
Flammability	Flammable
Combustion products	Water, carbon oxides

5. TEST CONDITIONS


ISO 291, 23 / 50 class 2

5.1 Specimen printing and conditioning

Parameter	Unit	Value
Nozzle temperature	°C	260
Bed temperature	°C	100
Printing speed	mm/s	80
Infill density	%	100
Layer height	mm	0.2
Specimen conditioning / annealing	°C / h	23 °C / 50 % RH for 24 h (ISO 291)

5.2 Specimen geometry (dimensions in millimetres)

Fig. 1 ISO 527-2 type 1A tensile specimen · top view, dimensions in mm



Section widths: $b_1 = 10.00 \pm 0.20$ (narrow section) · $b_2 = 20.00 \pm 0.20$ (grip ends) · $h = 4.00 \pm 0.20$ (thickness) · gauge length $L_0 = 75.0$ mm

Fig. 2 ISO 178 flexural specimen $80 \times 10 \times 4$ mm · three-point bending, span 64 mm




Fig. 3 ISO 179-1 Charpy notched specimen $80 \times 10 \times 4$ mm, 45° V-notch, depth 2.0 mm



6. STORAGE, HANDLING AND SAFETY

stewardship

Storage before use	Sealed bag with desiccant, 15 · 25 °C, below 50 % RH, away from direct sunlight and UV, away from ignition sources. Shelf life 24 months.
Storage after opening	Engineering grades absorb moisture noticeably. Reseal with desiccant and re-dry before critical prints: 70 · 80 °C for 4 · 6 h.
Symptoms of moisture	Popping and hissing at the nozzle, steam bubbles, rough extrusion, weak layer bonding, loss of impact strength. Dry the spool before changing settings.
Handling	Keep the spool on its holder and avoid sharp bends at the extruder inlet. Store away from solvents and strong oxidisers.
Ventilation	Printing releases a noticeable styrene or solvent-type odour and measurable VOC. Print in a well-ventilated area, preferably under extraction or with a filtered enclosure. Not for use in enclosed occupied spaces.
Fire and disposal	Combustible solid. Keep away from open flame and hot surfaces above 300 °C. Spool, bag and carton are recyclable; offcuts are not biodegradable. Provide adequate ventilation in case of fire · combustion yields carbon oxides.
Personal protection	No special protection required for normal use. Wear gloves when handling hot parts and safety glasses when cutting filament. For prolonged printing in a confined space, use an organic-vapour respirator.

7. ORDERING INFORMATION AND PACKAGING

commercial

Standard spool	1.00 kg net, Ø 200 mm, 68 mm hub bore, 4 locating holes. 0.25 / 0.50 / 3.00 kg spools on request.
Standard diameter	1.75 mm (2.85 mm on request). Tolerance per Section 2.
Export carton	10 rolls per carton, 5-ply corrugated. Carton net 10.0 kg, gross approx. 13.1 kg. Neutral print as standard.
Colour range	Stock colours as listed in Section 2. Custom colours matched to RAL, Pantone or a physical sample, subject to a minimum batch quantity.
OEM services	Spool label, shrink film print, spool material and colour, carton artwork and user manual. Artwork setup and MOQ are quoted per project.
Order confirmation	Every order is confirmed by a proforma invoice stating grade, colour, diameter, quantity, unit price, Incoterms and lead time.
Shipping and quality documents	Commercial invoice, packing list, bill of lading, certificate of origin and batch certificate of analysis as standard. RoHS / REACH declaration and safety data sheet on request.

Commercial terms shown here are indicative. The signed proforma invoice or sales contract prevails in case of any conflict.

8. DISCLAIMER AND REVISION CONTROL

The data in this document are typical values obtained from tests on standard specimens produced under the conditions described in Section 5. They are provided for material comparison and selection only and do not constitute a specification, warranty or guarantee of performance. Properties of an actual printed part depend on printer hardware, slicing parameters, part geometry, build orientation, ambient conditions and post-processing. WJ reserves the right to amend this document without notice. The buyer is responsible for verifying that the material is suitable for the intended application, including any regulatory or food-contact requirement.

8.1 How to read the data in this sheet

Typical, not minimum	The property tables describe specimens printed exactly as stated in Section 5. They describe the material, not a machined or moulded part.
Orientation matters	Values marked X·Y apply to specimens printed flat on the build plate. Z values are measured on parts printed standing up and are typically lower than X·Y. Design for the direction that carries the load.
Batch variation	Values carry a ± range where extrusion, pigment and ambient humidity vary between batches; colour masterbatch can shift impact strength noticeably. Where no deviation is given, the value is a single representative test.
Not a certificate	This sheet is not an inspection certificate, a Declaration of Conformity, or a certificate of analysis. Batch-specific CoA, RoHS / REACH declarations and safety data sheets are issued separately on request.

8.2 Revision history

Rev	Date	Description	Approved
V1.0	2026-08-01	First issue of PETG-CF technical data sheet.	QC / WJ

Prepared and released by

Shenzhen Wuju Creative Trading Co., Ltd.

Quality Control Department · Shenzhen, China

Authorised signature and company stamp



Shenzhen Wuju Creative Trading Co., Ltd.

Room 1617A5, 16th Floor, Building A, Galaxy Century Building, southwest of the intersection of Shennan Avenue and Caitian Road, Futian District, Shenzhen, China
Tel +86 137 2765 4403 · newtwizardbusiness@gmail.com · www.wj3dprinterfilamentofactory.com · Reg. no. 91440300MAECMMFU4Y

PETG CF - Data disclosure addendum

WJ-TDS-PETGCF-001 | Original revision V1.0 | Addendum A1 | 2026-08-01

TYPICAL REFERENCE VALUES / NO THIRD-PARTY REPORT

This technical data sheet provides typical reference values for material comparison and selection only. It is not an independent third-party test report and does not constitute a product specification, warranty or guarantee of performance. Test methods and specimen conditions are stated in the corresponding sections. The user must verify suitability for the intended application.

DOCUMENT CONTROL

This addendum supplements Section 8 of the original TDS. Numerical property values and processing ranges are unchanged. The original revision history remains unchanged. This TDS is not a certificate of analysis or conformity.